

PUBLICATION NUMBER : 07180025  
PUBLICATION DATE : 18-07-95 ✓

APPLICATION DATE : 24-12-93  
APPLICATION NUMBER : 05328716

APPLICANT : TOYOTA MOTOR CORP;

INVENTOR : MORIKAWA TAKASHI;

INT.CL. : C23C 8/12 C22C 14/00

TITLE : METHOD FOR OXIDIZING TI-AL INTERMETALLIC COMPOUND

ABSTRACT : PURPOSE: To provide a method for oxidizing a Ti Al intermetallic compound excellent in wear resistance.

CONSTITUTION: A Ti-Al intermetallic compound is subjected to oxidizing treatment under heating under the conditions of  $T+50\log H \geq 750$ ... inequality (a) and  $500+25 \times Al \geq T$ ... inequality (b) [where T: treating temp. ( $^{\circ}$ C), H: treating time (h) and Al: the content of Al (wt.%) in the material to be treated] in an atmosphere contg. at least oxygen. In the oxidizing treatment, it is subjected to oxidizing treatment under heating under conditions of  $25\log H+T+0.4 < 1150$ ... inequality (c) [where P: pressure (Torr)]. Thus, an oxidized film excellent in wear resistance can be obtd. on the surface of the Ti-Al intermetallic compound.

COPYRIGHT: (C)1995,JPO

Best Available Copy